

Dow Corning MOLYKOTE® 33 EXTREME LOW TEMPERATURE BEARING GREASE, MEDIUM

Category : Fluid , Lubricant , Silicone Base

Material Notes:

Phenyl-methyl silicone grease for extreme low temperatures Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-MOLYKOTE-33-EXTREME-LOW-TEMPERATURE-BEARING-GREASE-MEDIUM.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.970 g/cc	0.970 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Mechanical Properties	Metric	English	Comments
Four Ball Extreme Pressure, Weld Load	122.3 kg	269.7 lb (mass)	
Penetration P(60), 1/10 mm	280	280	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	204 °C	399 °F	
Minimum Service Temperature, Air	-70.0 °C	-94.0 °F	
Dropping Point	226 °C	439 °F	

Processing Properties	Metric	English	Comments
Shelf Life	60.0 Month	60.0 Month	

Descriptive Properties	Value	Comments
Color	white	
NLGI Number	2	
Thickening System	lithium soap	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China