

Dow Corning MOLYKOTE® 41 HIGH TEMPERATURE BEARING GREASE

Category : Fluid , Lubricant , Silicone Base

Material Notes:Phenyl-methyl silicone grease thickened with carbon black
Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-MOLYKOTE-41-HIGH-TEMPERATURE-BEARING-GREASE.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc @Temperature 25.0 °C	1.14 g/cc @Temperature 77.0 °F	

Mechanical Properties	Metric	English	Comments
Four Ball Extreme Pressure, Weld Load	152.9 kg	337.1 lb (mass)	
Penetration P(60), 1/10 mm	280	280	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	288 °C	550 °F	
Minimum Service Temperature, Air	-18.0 °C	-0.400 °F	
Dropping Point	>= 300 °C	>= 572 °F	

Processing Properties	Metric	English	Comments
Shelf Life	60.0 Month	60.0 Month	

Descriptive Properties	Value	Comments
Color	black	
NLGI Number	2	
Thickening System	carbon black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China