

Dow Corning OS-30

Category : Fluid

Material Notes:

Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-OS-30.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.850 g/cc @Temperature 25.0 °C	0.850 g/cc @Temperature 77.0 °F	
Viscosity	1.3 cP	1.3 cP	dynamic
Vapor Pressure	0.000573 bar @Temperature 25.0 °C	0.430 torr @Temperature 77.0 °F	
Surface Tension	17.3 dynes/cm	17.3 dynes/cm	

Thermal Properties	Metric	English	Comments
Melting Point	-68.0 °C	-90.4 °F	
Boiling Point	194 °C	381 °F	
Flash Point	57.0 °C	135 °F	closed cup

Processing Properties	Metric	English	Comments
Shelf Life	48.0 Month	48.0 Month	

Descriptive Properties	Value	Comments
Appearance	clear	
Hydrophobic	yes	
Water Resistant	yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China