

Dow Corning SE 4440 LP KIT

Category : Polymer , Adhesive , Thermoset , Silicone

Material Notes:

Two-part, grey, 1:1, addition cure gel, good thermal conductivity, low viscosity. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SE-4440-LP-KIT.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.01 g/cc	2.01 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Viscosity	3600 cP	3600 cP	dynamic

Mechanical Properties	Metric	English	Comments
Penetration P(60), 1/10 mm	58	58	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.830 W/m-K	5.76 BTU-in/hr-ft ² -°F	
Maximum Service Temperature, Air	150 °C	302 °F	
Minimum Service Temperature, Air	-45.0 °C	-49.0 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Dielectric Constant	6.2	6.2	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	13.0 kV/mm	330 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	30.0 min	0.500 hour	
	@Temperature 120 °C	@Temperature 248 °F	
Shelf Life	6.00 Month	6.00 Month	

Descriptive Properties	Value	Comments
Color	grey	

Descriptive Properties	Value	Comments
Self Leveling	yes	
Water Resistant	yes	
Working Time (min)	1440	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China