

Dow Corning SILASTIC® 9416/20E KIT PARTS A&B

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

30 Durometer, 2-part, 1 to 1 mix, opaque, Auto connector seal grade, Liquid Silicone Rubber. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-941620E-KIT-PARTS-AB.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.11 g/cc @Temperature 25.0 °C	1.11 g/cc @Temperature 77.0 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	16	16	
Tensile Strength, Ultimate	4.5001 MPa	652.68 psi	
Elongation at Break	995 %	995 %	
Tear Strength	11.01 kN/m	62.83 pli	
Compression Set	20 %	20 %	

Processing Properties	Metric	English	Comments
Pot Life	4320 min	4320 min	
Shelf Life	12.0 Month	12.0 Month	

Descriptive Properties	Value	Comments
Appearance	opaque	
Mix Ratio (X:1)	100	Base to Catalyst ETN

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China