

Dow Corning SILASTIC® L RTV SILICONE RUBBER BASE & CURING AGENT

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

Low durometer silicone mold making rubber recommended for use with rigid polyurethanes and can be used with polyesters and epoxies. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-L-RTV-SILICONE-RUBBER-BASE-CURING-AGENT.php

| Physical Properties | Metric | English | Comments |
|---------------------|----------------------|----------------------|-----------------|
| Specific Gravity | 1.27 g/cc | 1.27 g/cc | |
| | @Temperature 25.0 °C | @Temperature 77.0 °F | |
| Viscosity | 100000 cP | 100000 cP | mixing, dynamic |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|-----------|----------|----------|
| Hardness, Shore A | 34 | 34 | |
| Tensile Strength, Ultimate | 3.79 MPa | 550 psi | |
| Elongation at Break | 350 % | 350 % | |
| Tear Strength | 8.77 kN/m | 50.0 pli | |

| Descriptive Properties | Value | Comments |
|------------------------|-------|------------------|
| Color | green | |
| Mix Ratio (X:1) | 10 | Base to Catalyst |
| Working Time (min) | 60 | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China