

## Dow Corning SILASTIC® LC-60-2004 PART A&B KIT

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

### Material Notes:

60 Durometer, 2 parts, 1 to 1 mix, translucent, FDA 21 CFR 177.2600 and BfR, XV, molding and injection molding grade Liquid Silicone Rubber. Information provided by Dow Corning

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Dow-Corning-SILASTIC-LC-60-2004-PART-AB-KIT.php](http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-LC-60-2004-PART-AB-KIT.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	58	58	
Tensile Strength, Ultimate	9.322 MPa	1352 psi	
Elongation at Break	449 %	449 %	
Tear Strength	51.2 kN/m	292 pli	
Compression Set	17.1 %	17.1 %	

Processing Properties	Metric	English	Comments
Shelf Life	6.00 Month	6.00 Month	

Descriptive Properties	Value	Comments
Appearance	translucent	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China