

Dow Corning SILASTIC® LSR 9390-60 PARTS A&B

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

Material Notes:

60 Durometer, 2-part, 1 to 1 mix, oil resistant, tan Liquid Silicone Rubber for injection molding. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-LSR-9390-60-PARTS-AB.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------------------------------|-----------------------------------|----------|
| Specific Gravity | 1.47 g/cc @Temperature 25.0 °C | 1.47 g/cc @Temperature 77.0 °F | |
| Solids Content | 100 % | 100 % | |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|-----------|----------|----------|
| Hardness, Shore A | 59 | 59 | |
| Tensile Strength, Ultimate | 6.60 MPa | 957 psi | |
| Elongation at Break | 330 % | 330 % | |
| Tear Strength | 17.0 kN/m | 97.0 pli | |
| Compression Set | 15 % | 15 % | |

| Processing Properties | Metric | English | Comments |
|-----------------------|------------|------------|----------|
| Pot Life | 4320 min | 4320 min | |
| Shelf Life | 15.0 Month | 15.0 Month | |

| Descriptive Properties | Value | Comments |
|------------------------|-----------|----------------------|
| Color | off-white | |
| Mix Ratio (X:1) | 100 | Base to Catalyst ETN |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China