

Dow Corning SILASTIC® M-2 RTV SILICONE RUBBER BASE & CURING AGENT

Category : Polymer , Adhesive , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber , Silicone, RTV, Adhesive/Sealant Grade

Material Notes:

High durometer mold making silicone rubber suited for the reproduction of architectural, furniture components and prototypes. Silastic M is recommended for use with rigid and foam polyurethane and can be used with polyesters. Information provided by Dow Corning

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Corning-SILASTIC-M-2-RTV-SILICONE-RUBBER-BASE-CURING-AGENT.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.29 g/cc	1.29 g/cc	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Viscosity	80000 cP	80000 cP	dynamic

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	59	59	
Tensile Strength, Ultimate	4.48 MPa	650 psi	
Elongation at Break	200 %	200 %	
Tear Strength	14.9 kN/m	85.0 pli	

Descriptive Properties	Value	Comments
Color	blue	
Mix Ratio (X:1)	10	Base to Catalyst
Working Time (min)	90	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China