

Dow Engage® 8107 Polyolefin Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Description: Engage® 8107 polyolefin elastomer is a loose talc surface coated ethylene-octene copolymer. The talc is untreated and has a nominal 1µm particle size. This product offers the exceptional properties of Engage® 8100 with the added potential of handling these polymer pellets in rail cars. Engage® 8107 has excellent flow characteristics and performs well in a wide range of general purpose thermoplastic applications. It provides good impact properties in blends with polypropylene (PP) and polyethylene (PE). The talc addition significantly improves ability to handle the polymer, but severe blocking can occur if the material is stored under severe conditions (i.e., long duration, elevated temperatures, and/or high weight loadings). To minimize temperature effects, product should be stored at temperatures well below its melting point of 60°C. Information provided by manufacturer. This former DuPont Dow Elastomers product line is now produced by Dow Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Dow-Engage-8107-Polyolefin-Elastomer.php

Physical Properties	Metric	English	Comments
Density	0.870 g/cc	0.0314 lb/in ³	ASTM D792
Mooney Viscosity	23 @Temperature 121 °C	23 @Temperature 250 °F	ML 1 + 4; ASTM D1646
Melt Index of Compound	1.0 g/10 min @Load 2.16 kg, Temperature 190 °C	1.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	ASTM D2240
Hardness, Shore D	22	22	ASTM D2240
Tensile Strength, Ultimate	10.3 MPa	1490 psi	508 mm/min; ASTM D638
Tensile Strength, Yield	2.10 MPa	305 psi	508 mm/min; ASTM D638
Elongation at Break	820 %	820 %	508 mm/min; ASTM D638
2% Secant Modulus	0.0136 GPa	1.97 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Melting Point	60.0 °C	140 °F	DSC, 10°C/min; DuPont Test
Vicat Softening Point	39.0 °C	102 °F	ASTM D1525
Brittleness Temperature	<= -76.0 °C	<= -105 °F	ASTM D746

Descriptive Properties	Value	Comments
Comonomer Content	38 wt%	Dow Method (¹³C NMR/FTIR)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China