

## Dow LIGHTER™ C98 Polyethylene Terephthalate (PET) Resin

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET)

**Material Notes:**

LIGHTER™ resins are polyethylene terephthalate produced from PTA and MEG. These polymers are specifically designed for the production of beverage, food and other liquid containers and for thermoforming. LIGHTER™ C98 is preferred for bottles containing highly carbonated soft drinks, which require high mechanical properties and low gas permeability. It is recommended also for the production of extruded thermo formable sheets. Information provided by Dow

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Dow-LIGHTER-C98-Polyethylene-Terephthalate-PET-Resin.php](http://www.lookpolymers.com/polymer_Dow-LIGHTER-C98-Polyethylene-Terephthalate-PET-Resin.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.880 g/cc	0.0318 lb/in <sup>3</sup>	1/MA/1/008
Viscosity Measurement	0.83 - 0.87	0.83 - 0.87	[dl/g]; Intrinsic Viscosity; 1/MA/1/002
	98	98	[ml/g]; ISO Viscosity Number; ISO 1628/5
Crystallinity	>= 50 %	>= 50 %	1/MA/1/018

Thermal Properties	Metric	English	Comments
Melting Point	247 °C	477 °F	peak; 1/MA/1/007
Glass Transition Temp, Tg	78.0 °C	172 °F	1/MA/1/007

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.40 %	<= 0.40 %	1/MA/1/005

Descriptive Properties	Value	Comments
Acetaldehyde ppm, max	1	1/MA/1/004
Color, coordinate b, Max	2	1/MA/1/003
Fine Particles Content ppm, max	500	1/MA/1/001
Weight of 100 Granules g	1.5	1/MA/1/015

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China