

## Dow Latex LXC 8430NA Carboxylated Styrene-Butadiene Latex

Category : Polymer , Thermoplastic , Styrene-Butadiene

### Material Notes:

Applications: Latex LXC 8430NA for carpet is a firm-hand latex for residential and commercial carpet applications. Latex LXC 8430NA also has good rewet strength and can be used in formulations for print-base carpet (carpet that is back coated for dimensional stability and then dyed such as kitchen prints). Benefits: Firm hand High binding strength Excellent wet strength High tuft bind Self curing Low odor Excellent mechanical stability Excellent filler acceptance Information provided by Styron

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Dow-Latex-LXC-8430NA-Carboxylated-Styrene-Butadiene-Latex.php](http://www.lookpolymers.com/polymer_Dow-Latex-LXC-8430NA-Carboxylated-Styrene-Butadiene-Latex.php)

Physical Properties	Metric	English	Comments
Solids Content	52 %	52 %	
Particle Size	1.4 µm	1.4 µm	
pH	7.85	7.85	
Brookfield Viscosity	176 cP	176 cP	#2 @ 50 rpm

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-2.00 °C	28.4 °F	

Descriptive Properties	Value	Comments
Minimum film formation temperature	53.6°F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China