

## Dow Nordel® IP 4640 Molded Golf Grips

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

**Material Notes:**

FormulationNordel® IP 4640

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Dow-Nordel-IP-4640-Molded-Golf-Grips.php](http://www.lookpolymers.com/polymer_Dow-Nordel-IP-4640-Molded-Golf-Grips.php)

Physical Properties	Metric	English	Comments
Density	1.057 g/cc	0.03819 lb/in <sup>3</sup>	
Mooney Viscosity	49 @Temperature 100 °C	49 @Temperature 212 °F	ML 1 + 4

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	58	58	Vulcanizate, Press cured, TC95 +3min at 160°C
Tensile Strength, Ultimate	15.0 MPa	2180 psi	Vulcanizate, Press cured, TC95 +3min at 160°C
Elongation at Break	657 %	657 %	Vulcanizate, Press cured, TC95 +3min at 160°C
100% Modulus	0.00170 GPa	0.247 ksi	Vulcanizate, Press cured, TC95 +3min at 160°C
200% Modulus	0.00260 GPa	0.377 ksi	Vulcanizate, Press cured, TC95 +3min at 160°C
300% Modulus	0.00370 GPa	0.537 ksi	Vulcanizate, Press cured, TC95 +3min at 160°C
Tear Strength	27.8 kN/m	159 pli	Die C, Vulcanizate, Press cured, TC95 +3min at 160°C
Compression Set	88 % @Temperature 125 °C	88 % @Temperature 257 °F	Pellets cured MDR TC95 + 15 min at 160°C, 70 hr at 125°C; Method B

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-41.0 °C	-41.8 °F	Temperature Retraction, TR-10

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China