

DuPont™ Bynel® 50E806 Anhydride Modified Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

BYNEL® Series 5000 resins are anhydride-modified polypropylene resins. They are available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polypropylene (PP) resins. Physical properties of BYNEL Series 5000 resins are typical of polypropylene resins with similar density and melt flow rates. BYNEL 5000 series resins adhere to a variety of materials. They are most often used to adhere to PP, EVOH and polyamide. These resins are designed for applications in which EVOH or polyamide is melt coextruded with PP or PP copolymers. BYNEL 50E806 can be utilized pure, or can also be blended into PP for creating adhesion to barrier resins such as polyamide or EVOH. BYNEL 50E806 resin conforms with the Code of Federal Regulations, Title 21, Paragraph 175.105, covering the use of adhesive interlayers in composite packages for food use. This regulation describes adhesives which may be safely used as components of articles intended for use in packaging, transporting or holding food. This regulation requires that either (1) the adhesive is separated from the food by a functional barrier, or (2) the quantity of adhesive which contacts fatty or aqueous foods does not exceed the trace amounts at the seams or edges. Customers should satisfy themselves that the food contact material is serving as a functional barrier to the adhesive.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Bynel-50E806-Anhydride-Modified-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.880 g/cc	0.0318 lb/in ³	ASTM D792, ISO 1183
Melt Flow	25 g/10 min	25 g/10 min	ASTM D1238, ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Thermal Properties	Metric	English	Comments
Melting Point	97.0 °C	207 °F	Freezing Point; ASTM D3418
	140 °C	284 °F	ASTM D3418, ISO 3146
Vicat Softening Point	100 °C	212 °F	ASTM D1525, ISO 306

Processing Properties	Metric	English	Comments
Processing Temperature	<= 260 °C	<= 500 °F	
Feed Temperature	160 °C	320 °F	CoExtrusion with EVOH Processing
	160 °C	320 °F	CoExtrusion with Nylon Processing
Zone 2	210 °C	410 °F	CoExtrusion with EVOH Processing
	235 °C	455 °F	CoExtrusion with Nylon Processing
Zone 3	235 °C	455 °F	CoExtrusion with EVOH Processing

Processing Properties	260 °C Metric	500 °F English	CoExtrusion with Nylon Processing Comments
Zone 4	235 °C	455 °F	CoExtrusion with EVOH Processing
	260 °C	500 °F	CoExtrusion with Nylon Processing
Zone 5	235 °C	455 °F	CoExtrusion with EVOH Processing
	260 °C	500 °F	CoExtrusion with Nylon Processing
Adapter Temperature	235 °C	455 °F	CoExtrusion with EVOH Processing
	260 °C	500 °F	CoExtrusion with Nylon Processing
Die Temperature	235 °C	455 °F	CoExtrusion with EVOH Processing
	260 °C	500 °F	CoExtrusion with Nylon Processing
Melt Temperature	210 - 235 °C	410 - 455 °F	CoExtrusion with EVOH Processing
	<= 260 °C	<= 500 °F	CoExtrusion with Nylon Processing

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China