

DuPont™ Clysar® EHC Polyolefin Shrink Packaging Film, 150 Gauge (discontinued **)

Category: Polymer, Film, Thermoplastic, Polyethylene (PE), Polyolefin, Polyolefin, Film Grade, Polyolefin, Film Grade (Polyolefin), Polypropylene (PP)

Material Notes:

Data provided by DuPont Packaging Polymers. A biaxially oriented, heat-shrinkable copolymer film. It is a polypropylene and polyethylene-based film that is predominantly polypropylene. Used when excellent optics, high shrink force, and superb sheet flatness are essential. An excellent choice for doing multi-packs, high-speed applications, and static sealing.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Clysar-EHC-Polyolefin-Shrink-Packaging-Film-150-Gauge-nbspdiscontinued-.php

| Physical Properties | Metric | English | Comments |
|---------------------|----------------------------------|---------------------|--------------------------------------|
| Oxygen Transmission | 91.0 cc-mm/m ² -24hr- | 231 cc-mil/100 in²- | or 2400 cc/m²-24hr-atm for the film. |
| | atm | 24hr-atm | ASTM D3985 |

| Mechanical Properties | Metric | English | Comments |
|------------------------------------|--------------|-----------|---------------------------------------|
| Film Elongation at Break, MD | 130 % | 130 % | Average; ASTM D882 |
| Modulus of Elasticity | 0.770 GPa | 112 ksi | (stiffness), ASTM D882 |
| Coefficient of Friction, Dynamic | 0.35 | 0.35 | ASTM D1894 |
| Elmendorf Tear Strength MD | 8.0 g | 8.0 g | Orientation not specified; ASTM D1922 |
| Seal Strength | 4000 g/25 mm | 4000 g/in | F-88-68(73) |
| Film Tensile Strength at Break, MD | 131 MPa | 19000 psi | ASTM D882 |

| Optical Properties | Metric | English | Comments |
|--------------------|--------|---------|----------|
| Haze | 1.5 % | 1.5 % | |
| Gloss | 120 % | 120 % | |

| Processing Properties | Metric | English | Comments |
|------------------------|--------------|--------------|-----------------------------------|
| Processing Temperature | 177 - 232 °C | 351 - 450 °F | Optimum Tunnel temperature range. |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058



Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China