

**DuPont™ Clysar® EZ Polyolefin Shrink Packaging Film, 75 Gauge (discontinued \*\*)**

Category : Polymer , Film , Thermoplastic , Polyolefin , Polyolefin, Film Grade , Polyolefin, Film Grade (Polyolefin)

**Material Notes:**

Data provided by DuPont Packaging Polymers. A strong, clear, biaxially oriented, heat-shrinkable, multilayer film. Clysar®EZS is a high slip version of EZ. Used where a premium product appearance is required. Excellent optics, clean shrink appearance, and strong, durable seals are obtained on shadow boxes, irregular shapes, and general purpose overwrapping under a wide range of operating conditions.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Clysar-EZ-Polyolefin-Shrink-Packaging-Film-75-Gauge-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_DuPont-Clysar-EZ-Polyolefin-Shrink-Packaging-Film-75-Gauge-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Moisture Vapor Transmission	0.290 cc-mm/m <sup>2</sup> -24hr-atm	0.737 cc-mil/100 in <sup>2</sup> -24hr-atm	ASTM 1249
Water Vapor Transmission	15.0 g/m <sup>2</sup> /day	0.966 g/100 in <sup>2</sup> /day	ASTM 1249
Oxygen Transmission	103 cc-mm/m <sup>2</sup> -24hr-atm	262 cc-mil/100 in <sup>2</sup> -24hr-atm	or 5400 cc/m <sup>2</sup> -24hr-atm for the film. ASTM D3985

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	120 %	120 %	Average; ASTM D882
Modulus of Elasticity	0.440 GPa	63.8 ksi	(stiffness), ASTM D882
Coefficient of Friction, Dynamic	0.30	0.30	ASTM D1894
Elmendorf Tear Strength MD	27 g	27 g	Orientation not specified; ASTM D1922
Seal Strength	2750 g/25 mm	2750 g/in	F-88-68(73)
Film Tensile Strength at Break, MD	69.0 MPa	10000 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	2.3 %	2.3 %	
Gloss	140 %	140 %	

**Contact Songhan Plastic Technology Co.,Ltd.**Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China