

DuPont Elvaloy® 3427 AC Ethylene and 27% Butyl Acrylate Copolymer

Category : Polymer , Film , Thermoplastic , Ethylene Butyl Acrylate

Material Notes:

Elvaloy® 3427 AC can be used for coextrusion and compounding. It can also be used in extrusion coating. Elvaloy® 3427 AC is very soft and flexible, and has good adhesion to various polymers. It combines high melting point and good sealing properties. Elvaloy® 3427 AC is easily processed on standard equipment used for low density polyethylene. Information provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Elvaloy-3427-AC-Ethylene-and-27-Butyl-Acrylate-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.926 g/cc	0.0335 lb/in ³	ASTM D792 - ISO 1183
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D1238 - ISO 1133
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	81	81	ASTM D2240 - ISO 868
Hardness, Shore D	23	23	ASTM D2240 - ISO 868
Tensile Strength at Break	9.00 MPa	1310 psi	500 mm/min; ASTM D638 - ISO 527-2
Elongation at Break	900 %	900 %	500 mm/min; ASTM D638 - ISO 527-2
Tensile Modulus	0.0250 GPa	3.63 ksi	1 mm/min; ASTM D638 - ISO 527-2

Thermal Properties	Metric	English	Comments
Melting Point	94.0 °C	201 °F	By DSC; ASTM D3418 - ISO 3146
Vicat Softening Point	45.0 °C	113 °F	A ₅₀ (10N); ASTM D1525 - ISO 306

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	150 °C	302 °F	Extrusion lamination and extrusion coating
	150 °C	302 °F	Cast film
	150 °C	302 °F	Blown film
Middle Barrel Temperature	160 °C	320 °F	Blown film
	210 °C	410 °F	Cast film

Processing Properties	220 °C Metric	428 °F English	Extrusion lamination Comments
Front Barrel Temperature	170 °C	338 °F	Blown film
	250 °C	482 °F	Cast film
	290 °C	554 °F	Extrusion lamination
Adapter Temperature	180 °C	356 °F	Blown film
	250 °C	482 °F	Cast Film
	290 °C	554 °F	Extrusion lamination
Die Temperature	180 °C	356 °F	Blown film
	250 °C	482 °F	Cast film
	290 °C	554 °F	Extrusion lamination

Descriptive Properties	Value	Comments
BA-Content	27 wt. %	DuPont Method

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China