

DuPont Elvaloy® PTW Ethylene/N-Butyl Acrylate/Glycidyl Methacrylate Copolymer

Category : Polymer , Thermoplastic , Ethylene Butyl Acrylate

Material Notes:

Specialized copolymers deliver flexibility, toughness and weatherability to adhesives, plastics, highways and roofing. Availability: Globally Information provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Elvaloy-PTW-EthyleneN-Butyl-AcrylateGlycidyl-Methacrylate-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	ASTM D792 - ISO 1183
Melt Flow	12 g/10 min @Load 2.16 kg, Temperature 190 °C	12 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238 - ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73	73	ASTM D2240 - ISO 868
Tensile Strength at Break	5.20 MPa	754 psi	ASTM D638 - ISO 527-2
Elongation at Break	950 %	950 %	ASTM D638 - ISO 527-2

Thermal Properties	Metric	English	Comments
Melting Point	72.0 °C	162 °F	ASTM D3418 - ISO 3146
Glass Transition Temp, Tg	-55.0 °C	-67.0 °F	ASTM D3418

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China