

DuPont Elvax® 3130 Ethylene-Vinyl Acetate Copolymer Resin for Blown Film

Category : Polymer , Film , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate Copolymer (EVA), Film Grade

Material Notes:

12 wt% Vinyl Acetate. General Elvax® information: Elvax® packaging grade resins include low seal temperatures for use in coextrusions or for packaging temperature sensitive materials, excellent drawability for easy processing, good flex-crack resistance for liquid packaging, high toughness, low shrink for water bath applications, and excellent optical properties. It adheres to many materials. It is commonly used as a tie layer in certain coextrusions with dissimilar surfaces. Information provided by DuPont Packaging Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Elvax-3130-Ethylene-Vinyl-Acetate-Copolymer-Resin-for-Blown-Film.php

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in ³	ASTM D792
Moisture Vapor Transmission	0.910 cc-mm/m ² -24hr-atm	2.31 cc-mil/100 in ² -24hr-atm	g-mm/m ² -day; based on 1 mil (0.0254 mm) thick film; ASTM E96
Oxygen Transmission	158 cc-mm/m ² -24hr-atm @Thickness 0.0254 mm	401 cc-mil/100 in ² -24hr-atm @Thickness 0.00100 in	Based on 1 mil (0.0254 mm) thick film; ASTM D3985
Melt Flow	2.5 g/10 min	2.5 g/10 min	Condition not noted.; ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	580 %	580 %	MD-TD Average; ASTM D882
Film Elongation at Break, TD	580 %	580 %	MD-TD Average; ASTM D882
Impact	25.4	25.4	J/mm Spencer Impact; Average of MD and TD; ASTM D3420
Elmendorf Tear Strength, MD	2.99 g/micron	76.0 g/mil	Average of MD and TD; ASTM D1922
Film Tensile Strength at Break, MD	25.5 MPa	3700 psi	MD-TD Average; ASTM D882

Thermal Properties	Metric	English	Comments
Melting Point	75.0 °C	167 °F	Freezing Point via DSC/ASTM D3418
	95.0 °C	203 °F	Upon Melting via DSC/ASTM D3418
Vicat Softening Point	76.0 °C	169 °F	ASTM D1525

Optical Properties	Metric	English	Comments
Haze	5.0 %	5.0 %	ASTM D1003

Gloss	83 %	83 %	20°- ASTM D2457
Optical Properties	Metric	English	Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China