

## **DuPont™ Elvax® 3155 Ethylene Vinyl Acetate**

Category: Polymer, Thermoplastic, Ethylene Vinyl Acetate, Ethylene Vinyl Acetate Copolymer (EVA), Extrusion/Coating Grade

## **Material Notes:**

DuPont™ Elvax® 3155 is an extrudable ethylene-vinyl acetate copolymer resin available in pellet form for use in conventional extrusion equipment designed to process polyethylene resins. ELVAX® 3155 EVA Resin complies with Food and Drug Administration Regulation 21 CFR 177.1350(a)(1) - - Ethylene-vinyl acetate copolymers, subject to the limitations and requirements therein. This Regulation describes polymers that may be used in contact with food, subject to the finished food-contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (b)(1) of the Regulation.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_DuPont-Elvax-3155-Ethylene-Vinyl-Acetate.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in³	ASTM D792, ISO 1183
Melt Flow	25 g/10 min	25 g/10 min	ASTM D1238, ISO 1133
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Thermal Properties	Metric	English	Comments
Melting Point	63.0 °C	145 °F	Freezing Point; ASTM D3418, ISO 3146
	87.0 °C	189 °F	ASTM D3418, ISO 3146
Vicat Softening Point	55.0 °C	131 °F	ASTM D1525, ISO 306

Processing Properties	Metric	English	Comments
Processing Temperature	<= 230 °C	<= 446 °F	
Melt Temperature	175 - 230 °C	347 - 446 °F	Extrusion Coating

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China