

DuPont Elvax® 40L-08 Strippable Semiconductive Insulation Shield Formulation (discontinued **)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate

Material Notes:

Elvax® 40L-08 strippable semiconductive insulation shield. Information provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Elvax-40L-08-Strippable-Semiconductive-Insulation-Shield-Formulation-nbspdiscontinued-.php

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	10.89 MPa	1579 psi	After 7 days/121°C air oven, ASTM D573
	12.1 MPa	1750 psi	ASTM D412
Elongation at Break	210 %	210 %	After 7 days/121°C air oven; ASTM D573
	250 %	250 %	ASTM D412
Tear Strength	8.50 kN/m	48.5 pli	ASTM D470

Electrical Properties	Metric	English	Comments
Electrical Resistivity	116 ohm-cm	116 ohm-cm	ASTM D991-82
	@Temperature 130 °C	@Temperature 266 °F	
	174 ohm-cm	174 ohm-cm	ASTM D991-82
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	179 ohm-cm	179 ohm-cm	ASTM D991-82
	@Temperature 90.0 °C	@Temperature 194 °F	

Descriptive Properties	Value	Comments
Antioxidant	1.5 phr	
Conductive Black	50 phr	
Dicumyl Peroxide	2.5 phr	
Elvax® 40L-08	100 phr	
Stearic Acid	1 phr	
Triallyl Cyanurate	1 phr	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China