

**DuPont Elvax® 4260 Ethylene Vinyl Acetate (discontinued \*\*)**

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate

**Material Notes:**

DuPont™ Elvax® 4260 is an ethylene-vinyl acetate / acid terpolymer resin for use in industrial applications. Applications: Elvax® 4260 resins can be used for the following applications: adhesives, sealants, and wax blends. Information provided by DuPont™

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Elvax-4260-Ethylene-Vinyl-Acetate-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_DuPont-Elvax-4260-Ethylene-Vinyl-Acetate-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.955 g/cc	0.0345 lb/in <sup>3</sup>	ASTM D1505
Vinyl Acetate Content	28 %	28 %	
Melt Flow	6.0 g/10 min	6.0 g/10 min	modified; ASTM D1238, ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	ASTM D2240-ISO 868
Tensile Strength at Break	18.6 MPa	2700 psi	ASTM D1708
Elongation at Break	1000 %	1000 %	ASTM D1708
Tensile Modulus	0.0103 GPa	1.50 ksi	ASTM D1708

Thermal Properties	Metric	English	Comments
Ring & Ball Softening Point	158 °C	316 °F	ASTM E28

Descriptive Properties	Value	Comments
Cloud Point in Paraffin Wax, °C	99	10% Elvax® in fully refined paraffin wax, 146 AMP. Incompatible at temperatures up to 177°C.

**Contact Songhan Plastic Technology Co.,Ltd.**Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China