

## DuPont Elvax® 466 Ethylene Vinyl Acetate (discontinued \*\*)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate

### Material Notes:

DuPont™ Elvax® 466 is an ethylene-vinyl acetate copolymer resin for use in industrial applications. Applications: Elvax® 466 resins can be used for the following applications: adhesives, sealants, and wax blends. Information provided by DuPont™

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Elvax-466-Ethylene-Vinyl-Acetate-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_DuPont-Elvax-466-Ethylene-Vinyl-Acetate-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.941 g/cc	0.0340 lb/in <sup>3</sup>	ASTM D792-ISO 1183
Vinyl Acetate Content	18 %	18 %	
Melt Flow	1.5 g/10 min @Load 2.16 kg, Temperature 190 °C	1.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238, ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	91	91	ASTM D2240-ISO 868
Hardness, Shore D	41	41	ASTM D2240-ISO 868

Thermal Properties	Metric	English	Comments
Melting Point	87.0 °C	189 °F	DSC; ASTM D3417- ISO 3146
Vicat Softening Point	68.0 °C	154 °F	ASTM D1525, ISO 306
Brittleness Temperature	-100 °C	-148 °F	ASTM D746

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China