

DuPont Elvax® CM576 Ethylene Vinyl Acetate (discontinued **)

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate

Material Notes:

DuPont™ Elvax® CM576 is an ethylene-vinyl acetate copolymer resin for use in industrial applications. Specialty grades of Elvax® have the unusual combination of high vinyl acetate levels and low melt indices. Due to the high VA content, the polymers have low crystallinity and are relatively polar. Combined with high molecular weight (low MI), the polymers are almost "rubbery" in nature. These polymers can be blended with hydrocarbon waxes to give blends with unusual properties. The blends are mostly wax so they have excellent barrier properties to water as measured by MVTR. They are also relatively high in viscosity, due to the low MI of the polymer, so the blends have good physical properties. The high VA level means that these polymers are also soluble in organic solvents. The low MI gives them good heat resistance and this can be seen in the high Ring and Ball numbers. These polymers also can be used in other end-use markets that need the combination of high vinyl acetate and high molecular weight. One drawback is that the polymers are higher in gel than the standard grades of Elvax® to they cannot be used in some film markets. Applications: Elvax® CM576 resins can be used for the following applications: adhesives, sealants, and wax blends. Information provided by DuPont™

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Elvax-CM576-Ethylene-Vinyl-Acetate-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in ³	ASTM D792-ISO 1183
Vinyl Acetate Content	28 %	28 %	
Melt Flow	0.70 g/10 min @Load 2.16 kg, Temperature 190 °C	0.70 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238, ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	78	78	ASTM D2240-ISO 868
Tensile Strength at Break	22.1 MPa	3200 psi	ASTM D638 ISO 527-2
Elongation at Break	980 %	980 %	ASTM D638 ISO 527-2

Thermal Properties	Metric	English	Comments
Melting Point	47.0 °C	117 °F	Freezing Point; ASTM D3418
	71.0 °C	160 °F	ASTM D3417- ISO 3146
Ring & Ball Softening Point	210 °C	410 °F	ASTM E28

Descriptive Properties	Value	Comments
Cloud Point in Paraffin Wax, °C	68	10%10% poly/90% wax. Melt point of wax, 64°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China