

## DuPont™ Nomex® Type 993, 95 mil Nominal Thickness Medium-Density Aromatic Nylon Pressboard

Category : Polymer , Thermoplastic , Nylon , Nylon, Aromatic

### Material Notes:

Type 993 is a medium-density pressboard which offers a balance of rigidity and conformability along with outstanding saturability and excellent properties in air and oil. Typical applications include 3-dimensional parts such as V-rings, angle rings and spools, as well as barrier, gap spacers and core tubes. Information provided by DuPont

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Nomex-Type-993-95-mil-Nominal-Thickness-Medium-Density-Aromatic-Nylon-Pressboard.php](http://www.lookpolymers.com/polymer_DuPont-Nomex-Type-993-95-mil-Nominal-Thickness-Medium-Density-Aromatic-Nylon-Pressboard.php)

Physical Properties	Metric	English	Comments
Density	0.770 g/cc	0.0278 lb/in <sup>3</sup>	Calculated number using basis weight and thickness
Thickness	2400 microns	94.5 mil	ASTM D374, method D, using 17 N/cm <sup>2</sup>
Linear Mold Shrinkage	0.0080 cm/cm	0.0080 in/in	ASTM D3392
	@Temperature 105 °C	@Temperature 221 °F	
	0.012 cm/cm	0.012 in/in	ASTM D3392
	@Temperature 240 °C	@Temperature 464 °F	
Linear Mold Shrinkage, Transverse	0.011 cm/cm	0.011 in/in	ASTM D3392
	@Temperature 105 °C	@Temperature 221 °F	
	0.018 cm/cm	0.018 in/in	ASTM D3392
	@Temperature 240 °C	@Temperature 464 °F	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	44.0 MPa	6380 psi	ASTM D828
Film Tensile Strength at Yield, TD	37.4 MPa	5420 psi	ASTM D828
Film Elongation at Yield, MD	12 %	12 %	ASTM D828
Film Elongation at Yield, TD	12.1 %	12.1 %	ASTM D828

Electrical Properties	Metric	English	Comments
Dielectric Strength	20.0 kV/mm	508 kV/in	AC rapid rise in air; ASTM D149

Descriptive Properties	Value	Comments
------------------------	-------	----------

Basis Weight (g/m <sup>2</sup> ) Descriptive Properties	ASTM D3392 Value	Comments
--	---------------------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China