

DuPont Performance Polymers Delrin® 327UVE NC010 Acetal Homopolymer (Unverified Data**)

Category : Polymer , Thermoplastic , Acetal (POM)

Material Notes:

Delrin® 327UVE NC010 (formerly DE20554) is a medium-high viscosity acetal homopolymer with UV stabilizers having extremely low VOC emissions, developed for automotive interior applications. Information provided by DuPont Performance Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Delrin-327UVE-NC010-Acetal-Homopolymer-nbspUnverified-Data.php

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in ³	ISO 1183
Melt Flow	7.0 g/10 min @Load 2.16 kg, Temperature 190 °C	7.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133
Melt Index of Compound	6.0 g/10 min	6.0 g/10 min	cm ³ /10 min; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	71.0 MPa @Temperature 23.0 °C	10300 psi @Temperature 73.4 °F	ISO 527
Elongation at Break	40 % @Temperature 23.0 °C	40 % @Temperature 73.4 °F	nominal; ISO 527
	50 % @Temperature 23.0 °C	50 % @Temperature 73.4 °F	50mm/min; ISO 527
Elongation at Yield	22 % @Temperature 23.0 °C	22 % @Temperature 73.4 °F	ISO 527
Tensile Modulus	3.00 GPa @Temperature 23.0 °C	435 ksi @Temperature 73.4 °F	ISO 527
Charpy Impact Unnotched	35.0 J/cm ² @Temperature 23.0 °C	167 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU
Charpy Impact, Notched	1.00 J/cm ² @Temperature 23.0 °C	4.76 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Melting Point Thermal Properties	178 °C Metric	352 °F English	10°C/min: ISO 11357-1/-3 Comments
Deflection Temperature at 1.8 MPa (264 psi)	91.0 °C	196 °F	ISO 75-1/-2

Processing Properties	Metric	English	Comments
Melt Temperature	205 °C	401 °F	Optimum; Injection Molding
	200 - 210 °C	392 - 410 °F	Injection Molding
Mold Temperature	90.0 °C	194 °F	optimum; Injection Molding
	80.0 - 100 °C	176 - 212 °F	Injection Molding
Drying Temperature	80.0 °C	176 °F	Injection Molding
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	Injection Molding
Moisture Content	<= 0.20 %	<= 0.20 %	Injection Molding

Descriptive Properties	Value	Comments
Forms	Pellets	
Generic	Acetal (POM) Homopolymer	
Material Status	Preliminary Data	
Part Marking Code	>POM<	ISO 11469
Polymer Family	POM	
Polymer Type	POM Homopolymer	
Processing Method	Injection Molding	
Product Category	Low Emissions Resins	
	Unreinforced Resins	
	UV Resistant/Weatherable Resins	
Region Available - Global	Yes	
Resin Identification	POM	ISO 1043
RoHS Compliance	Contact Manufacturer	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China