

DuPont Performance Polymers Delrin® FG100AL NC010 Acetal Homopolymer (Unverified Data**)

Category : Polymer , Thermoplastic , Acetal (POM)

Material Notes:

Delrin® FG100AL is a high viscosity, lubricated acetal homopolymer resin, containing an advanced system of lubrication. It has been developed for consideration into applications such as parts for the food industry. Information provided by DuPont Performance Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Delrin-FG100AL-NC010-Acetal-Homopolymer-nbspUnverified-Data.php

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.020 cm/cm @Thickness 2.00 mm	0.020 in/in @Thickness 0.0787 in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.018 cm/cm @Thickness 2.00 mm	0.018 in/in @Thickness 0.0787 in	ISO 294-4
Melt Flow	2.5 g/10 min @Load 2.16 kg, Temperature 190 °C	2.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133
Melt Index of Compound	1.7 g/10 min @Load 2.16 kg, Temperature 190 °C	1.7 g/10 min @Load 4.76 lb, Temperature 374 °F	cm ³ /10 min; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	70.0 MPa @Temperature 23.0 °C	10200 psi @Temperature 73.4 °F	ISO 527
Elongation at Break	45 % @Temperature 23.0 °C	45 % @Temperature 73.4 °F	nominal; ISO 527
Elongation at Yield	18 % @Temperature 23.0 °C	18 % @Temperature 73.4 °F	ISO 527
Tensile Modulus	3.00 GPa @Temperature 23.0 °C	435 ksi @Temperature 73.4 °F	ISO 527
Flexural Modulus	2.80 GPa @Temperature 23.0 °C	406 ksi @Temperature 73.4 °F	ISO 178
	17.0 J/cm ²	80.9 ft-lb/in ²	

Charpy Impact Unnotched Mechanical Properties	Metric @ Temperature -30.0 °C	English @ Temperature -22.0 °F	ISO 179/1eU Comments
	25.0 J/cm ² @Temperature 23.0 °C	119 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU
Charpy Impact, Notched	0.700 J/cm ² @Temperature -30.0 °C	3.33 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eA
	0.900 J/cm ² @Temperature 23.0 °C	4.28 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	500 µm/m-°C @Temperature -40.0 - 23.0 °C	278 µin/in-°F @Temperature -40.0 - 73.4 °F	ISO 11359-1/-2
	500 µm/m-°C @Temperature 23.0 - 55.0 °C	278 µin/in-°F @Temperature 73.4 - 131 °F	ISO 11359-1/-2
	500 µm/m-°C @Temperature 55.0 - 100 °C	278 µin/in-°F @Temperature 131 - 212 °F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	100 µm/m-°C @Temperature -40.0 - 23.0 °C	55.6 µin/in-°F @Temperature -40.0 - 73.4 °F	ISO 11359-1/-2
	110 µm/m-°C @Temperature 23.0 - 55.0 °C	61.1 µin/in-°F @Temperature 73.4 - 131 °F	ISO 11359-1/-2
	150 µm/m-°C @Temperature 55.0 - 100 °C	83.3 µin/in-°F @Temperature 131 - 212 °F	ISO 11359-1/-2
Melting Point	178 °C	352 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	163 °C	325 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	97.0 °C	207 °F	ISO 75-1/-2

Processing Properties	Metric	English	Comments
Melt Temperature	215 °C	419 °F	Optimum; Injection Molding
	210 - 220 °C	410 - 428 °F	Injection Molding

Processing Properties	Metric	English	Comments
	80.0 - 100 °C	176 - 212 °F	Injection Molding
Drying Temperature	80.0 °C	176 °F	Injection Molding
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	Injection Molding
Moisture Content	<= 0.20 %	<= 0.20 %	Injection Molding

Descriptive Properties	Value	Comments
Appearance	Natural Color	
Features	Creep Resistance, Good	
	Friction, Low	
	Homopolymer	
	Impact Resistance, Good	
	Lubricated	
	Viscosity, High	
	Wear Resistance, Good	
Forms	Pellets	
Generic	Acetal (POM) Homopolymer	
Material Status	Preliminary Data	
Part Marking Code	>POM-S<	ISO 11469
Processing Method	Injection Molding	
Product Category	Food Contact Resins	
	Low Wear and Friction Resins	
	Unreinforced Resins	
Region Available - Global	Yes	
Resin Identification	POM-S	ISO 1043
RoHS Compliance	Contact Manufacturer	
Uses	Conveyors	
	Food Applications, Non-specific	

Descriptive Properties	Gears Value	Comments
Parts, Engineering		

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China