

DuPont Performance Polymers Delrin® FG150 NC010 Acetal (POM) (Unverified Data**)

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Homopolymer, Unreinforced

Material Notes:

High Viscosity Acetal Homopolymer Developed for Food Contact Applications Delrin FG150 NC010 is a high viscosity acetal homopolymer for extrusion processes. It has low die deposit and low porosity. It has been developed for consideration in applications Information provided by DuPont Performance Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Delrin-FG150-NC010-Acetal-POM-nbspUnverified-Data.php

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.018 cm/cm	0.018 in/in	ISO 294-4 2577
Linear Mold Shrinkage, Transverse	0.020 cm/cm	0.020 in/in	ISO 294-4 2577
Melt Flow	1.9 g/10 min	1.9 g/10 min	cm ³ /10min; ISO 1133
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	
	2.4 g/10 min	2.4 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	72.0 MPa	10400 psi	ISO 527-1/-2
Elongation at Break	40 %	40 %	Nominal; ISO 527-1/-2
Elongation at Yield	22 %	22 %	ISO 527-1/-2
Tensile Modulus	3.10 GPa	450 ksi	ISO 527-1/-2
Flexural Modulus	2.90 GPa	421 ksi	ISO 178
Izod Impact, Notched (ISO)	10.0 kJ/m ²	4.76 ft-lb/in ²	ISO 180/1A
Charpy Impact, Notched	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179/1eA
	0.900 J/cm ²	4.28 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	110 µm/m-°C	61.1 µin/in-°F	ISO 11359-1/-2

Thermal Properties CTE, linear, transverse to Flow	Metric 100 µm/m-°C	English 500 µin/in-°F	Comments ISO 11359-1/-2
Melting Point	178 °C	352 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	165 °C	329 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	97.0 °C	207 °F	ISO 75-1/-2
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	IEC 60695-11-10

Descriptive Properties	Value	Comments
Additives	Release agent	
Delivery Form	Pellets	
Part Marking Code	>POM<	ISO 11469
Processing	Injection Moulding	
	Other Extrusion	
	Profile Extrusion	
	Sheet Extrusion	
Regional Availability	Asia Pacific	
	Europe	
	Global	
	Near East/Africa	
	North America	
	South and Central America	
Resin Identification	POM	ISO 1043
UL recognition	UL	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China