

## **DuPont Performance Polymers Hypalon® CP-826 Adhesion Primer, General Description (discontinued \*\*)**

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE), Chlorosulfonated Polyethylene Rubber

## **Material Notes:**

Hypalon CP 826 is a chlorinated, maleic anhydride grafted polypropylene resin. Suggested End Uses: Adhesion primer for:PolypropylenePolypropylene blends with TPOs (auto bumpers)Polyurethane foam, (athletic shoe construction)EVA with high levels of PE (athletic shoes)Main Features: Hypalon CP 826 has been developed to have excellent adhesion to polypropylene and blends containing polypropylene. It can be used in dilute solutions as a wash primer or tie layer between materials that are difficult to adhere. It can also be used as an adhesion modifier for coatings, adhesives and inks because of its solubility in commonly used solvents. Hypalon CP 826 is offered in solid form. Information provided by manufacturer. This former DuPont Dow Elastomers product line is now produced by DuPont Performance Elastomers.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_DuPont-Performance-Polymers-Hypalon-CP-826-Adhesion-Primer-General-Description-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in³	
Viscosity	260 cP	260 cP	

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	30.0 °C	86.0 °F	

Optical Properties	Metric	English	Comments
Gardner Color Number	<= 1.0	<= 1.0	at 20% in Xylene

Descriptive Properties	Value	Comments
Chlorine Content	30 wt%	
Product Form	Chips	
Saponification number	16.5 mg KOH/g	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China