

## DuPont Performance Polymers Hytrel® PC948 NC010 Polyester Elastomer TPC-ET (Unverified Data\*\*)

Category : Polymer , Thermoplastic , Polyester, TP , Polyester Thermoplastic Elastomer

### Material Notes:

40 Shore D High Performance Polyester Elastomer Developed for the Healthcare Industry Hytrel SC948 NC010 is a low modulus grade with nom. durometer hardness of 40D contains non-discoloring stabilizer and can be processed by various thermoplastic procesInformation provided by DuPont Performance Polymers

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Performance-Polymers-Hytrel-PC948-NC010-Polyester-Elastomer-TPC-ET-nbspUnverified-Data.php](http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Hytrel-PC948-NC010-Polyester-Elastomer-TPC-ET-nbspUnverified-Data.php)

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in <sup>3</sup>	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	<= 40	<= 40	ISO 868
Tensile Strength at Break	22.0 MPa	3190 psi	ISO 527-1/-2
Elongation at Break	>= 300 %	>= 300 %	ISO 527-1/-2
Charpy Impact, Notched	NB	NB	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	193 °C	379 °F	10°C/min; ISO 11357-1/-3

Descriptive Properties	Value	Comments
Delivery Form	Pellets	
Part Marking Code	>TPC-ET<	ISO 11469
Processing	Casting	
	Film Extrusion	
	Injection Moulding	
	Other Extrusion	
	Profile Extrusion	
	Sheet Extrusion	
Regional Availability	Asia Pacific	

Descriptive Properties	Value	Comments
	Global	
	Near East/Africa	
	North America	
	South and Central America	
Resin Identification	TPC-ET	ISO 1043
Special Characteristics	Light stabilised or stable to light	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China