

DuPont Performance Polymers Neoprene 115 Polychloroprene (discontinued **)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Main feature: Mechanical stability methacrylic acid copolymer reactive. Principal uses include: Coatings, Modifiers, Asphalt, Concrete. Solids content: 47%. Initial pH: 7. Surface tension: 47 dyne/cm. Polymer type: Medium-low gel. Emulsifying agent: PVOH. Very slow crystallization rate. Wet Gel Properties: Fast cure rate. Low modulus. General Neoprene Latex Information: Neoprene latexes are aqueous colloidal dispersions of polychloroprene or of copolymers of chloroprene with other monomers such as methacrylic acid or 2,3-dichloro-1,3-butadiene. They are available in both anionic and nonionic surfactant systems. All neoprene latexes have a unique combination of inherent characteristics including excellent film formation; high cohesive strength without curing; elastomeric properties over a wide temperature range; and considerable resistance to degradation from chemical or environmental exposure. Uses include adhesives, binders, coatings, dipped goods, elasticized asphalt and concrete, and foam. Information provided by DuPont Dow Elastomers. This former DuPont Dow Elastomers product line is now produced by DuPont Performance Elastomers. This grade is not a part of the standard product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Neoprene-115-Polychloroprene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.109 g/cc	0.04007 lb/in ³	Latex
	1.24 g/cc	0.0448 lb/in ³	Polymer
Brookfield Viscosity	350 cP	350 cP	#1 spindle; 30 rpm
	500 cP	500 cP	#1 spindle; 30 rpm.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China