

## DuPont Performance Polymers Neoprene 750 Polychloroprene (discontinued \*\*)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Main feature: Excellent flexibility. Principal uses include: Dipped goods, Thread (Non-woven fabrics), Adhesives (Contact, Cord, Construction, Pressure Sensitive). Solids content: 50%. Initial pH: 12.5. Surface tension: 40 dyne/cm. Polymer type: Medium gel. Emulsifying agent: Potassium salt of disproportionated resin. Slow crystallization rate. Wet Gel Properties: Very high tensile strength. High elongation. Medium cure rate. Low modulus. General Neoprene Latex Information: Neoprene latexes are aqueous colloidal dispersions of polychloroprene or of copolymers of chloroprene with other monomers such as methacrylic acid or 2,3-dichloro-1,3-butadiene. They are available in both anionic and nonionic surfactant systems. All neoprene latexes have a unique combination of inherent characteristics including excellent film formation; high cohesive strength without curing; elastomeric properties over a wide temperature range; and considerable resistance to degradation from chemical or environmental exposure. Uses include adhesives, binders, coatings, dipped goods, elasticized asphalt and concrete, and foam. Information provided by DuPont Dow Elastomers. This former DuPont Dow Elastomers product line is now produced by DuPont Performance Elastomers.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Performance-Polymers-Neoprene-750-Polychloroprene-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Neoprene-750-Polychloroprene-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in <sup>3</sup>	Latex
	1.23 g/cc	0.0444 lb/in <sup>3</sup>	Polymer
Brookfield Viscosity	10 cP	10 cP	# 1 spindle; 6 rpm.
	10 cP	10 cP	# 1 spindle; 30 rpm.

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China