

## DuPont Performance Polymers Sorona® 3030GV BK001 Polytrimethylene Terephthalate (PTT)

Category : Polymer , Thermoplastic , Polyester, TP , Polytrimethylene Terephthalate (PTT)

### Material Notes:

30% Glass Reinforced Renewably Sourced Polytrimethylene Terephthalate Sorona 3030GV BK001 is a 30% glass reinforced black PTT resin containing 25% renewably sourced ingredients by weight (37% based on polymer only) with low warpage and superior strength. Information provided by DuPont Performance Polymers

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Performance-Polymers-Sorona-3030GV-BK001-Polytrimethylene-Terephthalate-PTT.php](http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Sorona-3030GV-BK001-Polytrimethylene-Terephthalate-PTT.php)

Physical Properties	Metric	English	Comments
Density	1.56 g/cc	0.0564 lb/in <sup>3</sup>	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	142 MPa	20600 psi	ISO 527-1/-2
Elongation at Break	2.0 %	2.0 %	ISO 527-1/-2
Tensile Modulus	10.6 GPa	1540 ksi	ISO 527-1/-2
Flexural Strength	215 MPa	31200 psi	ISO 178
Flexural Modulus	9.40 GPa	1360 ksi	ISO 178
Charpy Impact Unnotched	4.50 J/cm <sup>2</sup>	21.4 ft-lb/in <sup>2</sup>	ISO 179/1eU
Charpy Impact, Notched	0.700 J/cm <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	227 °C	441 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	226 °C	439 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	IEC 60695-11-10
	@Thickness 0.800 mm	@Thickness 0.0315 in	
Oxygen Index	21 %	21 %	ISO 4589-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	3.00e+14 ohm	3.00e+14 ohm	IEC 60093
Dielectric Constant	4.1	4.1	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	4.3	4.3	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dissipation Factor	0.0015	0.0015	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	0.0155	0.0155	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	300 V	300 V	IEC 60112

Descriptive Properties	Value	Comments
Part Marking Code	>PTT-GF30<	ISO 11469
Processing	Injection Moulding	
Regional Availability	Asia Pacific	
	Europe	
	Global	
	Near East/Africa	
	North America	
	South and Central America	
Resin Identification	PTT-GF30	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China