

DuPont Performance Polymers VTR 8505 Peroxide Cured Fluoroelastomer (FKM) Formulation (discontinued **)

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

FormulationViton® 8505

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-VTR-8505-Peroxide-Cured-Fluoroelastomer-FKM-Formulation-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Mooney Viscosity	20 @Temperature 121 °C	20 @Temperature 250 °F	ML-10 (gum)-Akron data

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	68	68	Cured 7 min at 177°C and Post Cured 2 hr at 232°C
Tensile Strength, Ultimate	16.2 MPa	2350 psi	Cured 7 min at 177°C and Post Cured 2 hr at 232°C
Elongation at Break	254 %	254 %	Cured 7 min at 177°C and Post Cured 2 hr at 232°C
Modulus of Elasticity	0.000700 GPa	0.102 ksi	10% Modulus, Cured 7 min at 177°C and Post Cured 2 hr at 232°C
100% Modulus	0.00370 GPa	0.537 ksi	Cured 7 min at 177°C and Post Cured 2 hr at 232°C
Compression Set	20 % @Temperature 200 °C	20 % @Temperature 392 °F	Method B, O-rings 70 hr at 200°C (Post Cured 2 hr at 232°C)

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-32.8 °C	-27.0 °F	DSC, modulated

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China