

DuPont Performance Polymers Zytel® FG50 NC010 Nylon 66 (Unverified Data**)

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Unreinforced High Viscosity Polyamide 66 with Developed for Food Contact Applications Information provided by DuPont Performance Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Zytel-FG50-NC010-Nylon-66-nbspUnverified-Data.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	DAM; ISO 1183
Water Absorption	8.5 %	8.5 %	DAM; Sim. to ISO 62
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Moisture Absorption	2.70 %	2.70 %	DAM; Sim. to ISO 62
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Viscosity Test	300 cm ³ /g	300 cm ³ /g	DAM; ISO 307 1157 1628
Linear Mold Shrinkage, Flow	0.015 cm/cm	0.015 in/in	DAM; ISO 294-4 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	54.0 MPa	7830 psi	50%RH; ISO 527-1/-2
	82.0 MPa	11900 psi	DAM; ISO 527-1/-2
Elongation at Break	>= 50 %	>= 50 %	DAM; Nominal; ISO 527-1/-2
	>= 50 %	>= 50 %	50%RH; Nominal; ISO 527-1/-2
Elongation at Yield	4.5 %	4.5 %	DAM; ISO 527-1/-2
	28 %	28 %	50%RH; ISO 527-1/-2
Tensile Modulus	1.20 GPa	174 ksi	50%RH; ISO 527-1/-2
	3.00 GPa	435 ksi	DAM; ISO 527-1/-2
Charpy Impact Unnotched	NB	NB	DAM; ISO 179/1eU
	NB	NB	50%RH; ISO 179/1eU
	NB	NB	DAM; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Mechanical Properties	Metric	English	Comments
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.700 J/cm ²	3.33 ft-lb/in ²	DAM; ISO 179/1eA
	2.90 J/cm ²	13.8 ft-lb/in ²	50%RH; ISO 179/1eA
	0.400 J/cm ²	1.90 ft-lb/in ²	50%RH; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.600 J/cm ²	2.86 ft-lb/in ²	DAM; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	100 µm/m-°C	55.6 µin/in-°F	DAM; ISO 11359-1/-2
CTE, linear, Transverse to Flow	100 µm/m-°C	55.6 µin/in-°F	DAM; ISO 11359-1/-2
Melting Point	263 °C	505 °F	DAM; 10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	205 °C	401 °F	DAM; ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	74.0 °C	165 °F	DAM; ISO 75-1/-2
Vicat Softening Point	245 °C	473 °F	DAM; 50°C/h 50N; ISO 306

Descriptive Properties	Value	Comments
Delivery Form	Pellets	
Processing	Casting	
	Coatable	
	Film Extrusion	
	Injection Moulding	
	Other Extrusion	
	Profile Extrusion	
	Sheet Extrusion	
Regional Availability	Europe	
	Near East/Africa	
	North America	

Descriptive Properties	South and Central America Value	Comments
------------------------	------------------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China