

**DuPont™ Sclairfilm® GL-1 LLDPE Film, Laminating, 38.1 μm Thickness
(discontinued **)**

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Film Grade

Material Notes:

Data provided by DuPont Packaging Polymers. A general purpose linear low density polyethylene sealant film designed for less critical sealing applications than type SL. It provides good heat seal and hot tack characteristics along with good physical strength and opticals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Sclairfilm-GL-1-LLDPE-Film-Laminating-381-m-Thickness-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in ³	
Moisture Vapor Transmission	0.470 cc-mm/m ² -24hr-atm	1.19 cc-mil/100 in ² -24hr-atm	ASTM E96 Procedure E
Water Vapor Transmission	12.4 g/m ² /day	0.799 g/100 in ² /day	ASTM E96 Procedure E
Oxygen Transmission	236 cc-mm/m ² -24hr-atm	599 cc-mil/100 in ² -24hr-atm	or 6200 cc/m ² -24hr-atm for the film. ASTM D3985

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	600 %	600 %	ASTM D882
Tensile Modulus	0.190 GPa	27.6 ksi	ASTM D882
Dart Drop Test	80.0 g	0.176 lb	
Film Tensile Strength at Break, MD	32.0 MPa	4640 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	9.0 %	9.0 %	ASTM D1003
Gloss	80 %	80 %	20°; ASTM D2457

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China