

DuPont™ Surlyn® 1652-1 Zinc Ionomer Resin for Blown/Cast Film and Extrusion Coating (discontinued **)

Category : Polymer , Film , Thermoplastic , Ionomer , Ionomer, Film Grade

Material Notes:

Surlyn® 1652-1 is an ionomer resin available for use in blown/cast film and extrusion coating operations. It can be used in both extrusion and coextrusion equipment designed to process polyethylene resins. Applications: Meat, poultry, seafood and cheese packaging; Cereal liners; Medical/pharmaceutical packaging; Powdered/granular food and nonfood pouches; Edible oil, motor oil, and other liquid product pouches; Snack structures Data provided by the manufacturer, DuPont Packaging.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Surlyn-1652-1-Zinc-Ionomer-Resin-for-BlownCast-Film-and-Extrusion-Coating-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	ASTM D792
Melt Flow	4.5 g/10 min @Load 2.16 kg, Temperature 190 °C	4.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	500 %	500 %	ASTM D882
Film Elongation at Break, TD	400 %	400 %	ASTM D882
Secant Modulus, MD	0.160 GPa	23.2 ksi	ASTM D882
Secant Modulus, TD	0.0450 GPa	6.53 ksi	ASTM D882
Impact	220	220	Spencer Impact in J/cm; ASTM D3420
Elmendorf Tear Strength, MD	3.50 g/micron	88.9 g/mil	
Elmendorf Tear Strength, TD	3.70 g/micron	94.0 g/mil	
Dart Drop	7.90 g/micron	201 g/mil	ASTM D1709B
Seal Strength	<= 2700 g/25 mm	<= 2700 g/in	Varies with seal bar temp.
Hot Tack Strength	<= 2000 g/25 mm	<= 2000 g/in	Varies with seal bar temp.; Packforsk Method
Film Tensile Strength at Break, MD	30.0 MPa	4350 psi	ASTM D882
Film Tensile Strength at Break, TD	30.0 MPa	4350 psi	ASTM D882

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Melting Point Thermal Properties	100 °C Metric	212 °F English	DSC: ASTM D3418 Comments
Vicat Softening Point	79.0 °C	174 °F	ASTM D1525

Optical Properties	Metric	English	Comments
Haze	3.5 %	3.5 %	ASTM D1003
Gloss	60 %	60 %	20°; ASTM D2457

Processing Properties	Metric	English	Comments
Melt Temperature	177 °C	351 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China