## DuPont Teijin Films Melinex® 453 Polyester Film, 500 Gauge

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyester Film

## Material Notes:

Melinex® 453 is an excellent handling, high clarity film with one side pre-treated to promote adhesion to most printing inks and Industrial coatings.Typical Applications: Melinex® 453 is used as a base for pressure sensitive labels, general industrial coatings and applied window films.Approvals: UL Recognition - Melinex® 453 has been registered with Underwriters LaboratoriesInformation provided by DuPont.

## Order this product through the following link: http://www.lookpolymers.com/polymer\_DuPont-Teijin-Films-Melinex-453-Polyester-Film-500-Gauge.php

| Mechanical Properties              | Metric   | English   | Comments   |
|------------------------------------|----------|-----------|------------|
| Film Tensile Strength at Yield, MD | 96.5 MPa | 14000 psi | ASTM D882A |
| Film Tensile Strength at Yield, TD | 96.5 MPa | 14000 psi | ASTM D882A |
| Film Elongation at Break, MD       | 150 %    | 150 %     | ASTM D882A |
| Film Elongation at Break, TD       | 100 %    | 100 %     | ASTM D882A |
| Coefficient of Friction, Dynamic   | 0.40     | 0.40      | ASTM D1894 |
| Film Tensile Strength at Break, MD | 193 MPa  | 28000 psi | ASTM D882A |
| Film Tensile Strength at Break, TD | 248 MPa  | 36000 psi | ASTM D882A |

| Thermal Properties | Metric                               | English                                  | Comments     |
|--------------------|--------------------------------------|--|--------------|
| Shrinkage, MD      | 2.5 %                                | 2.5 %                                    | Unrestrained |
|                    | @Temperature 190 °C,<br>Time 300 sec | @Temperature 374 °F,<br>Time 0.0833 hour |              |
| Shrinkage, TD      | 1.0 %                                | 1.0 %                                    | Unrestrained |
|                    | @Temperature 190 °C,<br>Time 300 sec | @Temperature 374 °F,<br>Time 0.0833 hour |              |

| Optical Properties    | Metric | English | Comments        |
|-----------------------|--------|---------|-----------------|
| Haze                  | 0.60 % | 0.60 %  | ASTM D1003      |
| Transmission, Visible | 88 %   | 88 %    | TLT; ASTM D1003 |

| Descriptive Properties | Value                    | Comments |
|------------------------|--------------------------|----------|
| Yield (nominal)        | 4000 in <sup>2</sup> /lb |          |

## Contact Songhan Plastic Technology Co.,Ltd.



Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China