

## DuPont Teijin Films Melinex® 581 Polyester Film

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyester Film

**Material Notes:**

A super clear, one side C-Sub pretreated film for adhesion of hydrophilic coatings. Approvals: UL Recognition - Product has been registered with Underwriters Laboratories. Information provided by DuPont.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Teijin-Films-Melinex-581-Polyester-Film.php](http://www.lookpolymers.com/polymer_DuPont-Teijin-Films-Melinex-581-Polyester-Film.php)

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	100 MPa	14500 psi	ASTM D882A
Film Elongation at Break, MD	170 %	170 %	ASTM D882A
Film Elongation at Break, TD	120 %	120 %	ASTM D882A
Coefficient of Friction, Dynamic	0.50	0.50	A-B; ASTM D1894
Film Tensile Strength at Break, MD	193 MPa	28000 psi	ASTM D882A
Film Tensile Strength at Break, TD	241 MPa	35000 psi	ASTM D882A

Thermal Properties	Metric	English	Comments
Shrinkage, MD	2.5 %	2.5 %	Unrestrained
	@Temperature 190 °C, Time 300 sec	@Temperature 374 °F, Time 0.0833 hour	
Shrinkage, TD	1.0 %	1.0 %	Unrestrained
	@Temperature 190 °C, Time 300 sec	@Temperature 374 °F, Time 0.0833 hour	

Optical Properties	Metric	English	Comments
Transmission, Visible	88 %	88 %	TLT; ASTM D1003
	@Thickness 0.127 mm	@Thickness 0.00500 in	
	89 %	89 %	
	@Thickness 0.102 mm	@Thickness 0.00400 in	TLT; ASTM D1003
	90 %	90 %	TLT; ASTM D1003
	@Thickness 0.0635 mm	@Thickness 0.00250 in	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China