

## DuPont Teijin Films Melinex® S Polyester Film, 75 Gauge

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyester Film

### Material Notes:

Melinex® S is a general purpose film which combines excellent handling characteristics with a slightly hazy appearance. It is available in specific thicknesses from 48 - 500 gauge, and is used for the full range of Melinex® applications. Approvals: UL 94 VTM-2 - for 92 - 500 gauge (0.023 - 0.13mm) and UL Recognition - Product has been registered with Underwriters Laboratories. Information provided by DuPont.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_DuPont-Teijin-Films-Melinex-S-Polyester-Film-75-Gauge.php](http://www.lookpolymers.com/polymer_DuPont-Teijin-Films-Melinex-S-Polyester-Film-75-Gauge.php)

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	100 MPa	14500 psi	ASTM D882A
Film Tensile Strength at Yield, TD	99.3 MPa	14400 psi	ASTM D882A
Film Elongation at Break, MD	160 %	160 %	ASTM D882A
Film Elongation at Break, TD	100 %	100 %	ASTM D882A
Coefficient of Friction, Dynamic	0.40	0.40	A-B; ASTM D1894
Film Tensile Strength at Break, MD	200 MPa	29000 psi	ASTM D882A
Film Tensile Strength at Break, TD	255 MPa	37000 psi	ASTM D882A

Thermal Properties	Metric	English	Comments
Shrinkage, MD	3.5 %	3.5 %	Unrestrained
	@Temperature 190 °C, Time 300 sec	@Temperature 374 °F, Time 0.0833 hour	
Shrinkage, TD	3.5 %	3.5 %	Unrestrained
	@Temperature 190 °C, Time 300 sec	@Temperature 374 °F, Time 0.0833 hour	

Optical Properties	Metric	English	Comments
Haze	5.3 %	5.3 %	ASTM D1003
Transmission, Visible	88 %	88 %	TLT; ASTM D1003

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

<b>Electrical Properties</b>	<b>1.00e+17 ohm-cm Metric</b>	<b>1.00e+17 ohm-cm English</b>	<b>Comments</b>
<b>Volume Resistivity</b>	@Temperature 25.0 °C, Time 100 sec	@Temperature 77.0 °F, Time 0.0278 hour	100 V DC; ASTM D257
<b>Surface Resistivity per Square</b>	1.00e+15 ohm @Temperature 25.0 °C	1.00e+15 ohm @Temperature 77.0 °F	500 V DC @ 50% RH; ASTM D257
<b>Dielectric Strength</b>	320.2 kV/mm	8133 kV/in	0.25 inch electrodes in dry air @25°C; ASTM D149-81
<b>Dielectric Breakdown</b>	6100 V	6100 V	0.25 inch electrodes in dry air @25°C; ASTM D149-81

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China