

DuPont Teijin Films Mylar® S2 Polyester Film, 750 Gauge

Category : Polymer , Film , Thermoplastic , Polyester, TP , Polyester Film

Material Notes:

Mylar® S2 is a slightly hazy film designed for use in the production of drumheads. It has low haze, excellent impact resistance, and balanced physical properties, resulting in consistent tonal qualities. Information provided by DuPont.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Teijin-Films-Mylar-S2-Polyester-Film-750-Gauge.php

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/in ³	Typical Mylar®; ASTM D1505

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	170 %	170 %	ASTM D882A
Film Elongation at Break, TD	130 %	130 %	ASTM D882A
Film Tensile Strength at Break, MD	179 MPa	26000 psi	ASTM D882A
Film Tensile Strength at Break, TD	207 MPa	30000 psi	ASTM D882A

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	1.17 J/g-°C	0.280 BTU/lb-°F	Typical Mylar®
Melting Point	254 °C	489 °F	Typical Mylar® via DSC
Shrinkage, MD	1.1 % @Temperature 150 °C, Time 1800 sec	1.1 % @Temperature 302 °F, Time 0.500 hour	Unrestrained
Shrinkage, TD	1.4 % @Temperature 150 °C, Time 1800 sec	1.4 % @Temperature 302 °F, Time 0.500 hour	Unrestrained

Optical Properties	Metric	English	Comments
Haze	16 %	16 %	ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China