

E-Polymers EFLEX® S1040 General

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrenic TPE , Polypropylene (PP)

Material Notes:

S-series (SBS, SEBS compound resins): E-FLEX S series resins are based on SBS/SEBS/SEEPS/PP exhibiting excellent high and low temperature resistance and easy processing with conventional thermoplastic equipment. Overmolding grade is based on SEBS/SEEPS/engineering plastics and exhibit excellent adhesion to engineering plastics as PA, PC, ABS, PC/ABS, PBT. It has product lines for general grade, transparent grade, overmolding grade, high temperature grade, medical grade and extrusion grade. Information Provided by E-Polymers Co., Ltd.

Order this product through the following link: http://www.lookpolymers.com/polymer_E-Polymers-EFLEX-S1040-General.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------------------------------------|--------------------------------------|------------|
| Specific Gravity | 1.10 g/cc | 1.10 g/cc | ASTM D792 |
| Melt Flow | 7.1 g/10 min | 7.1 g/10 min | ASTM D1238 |
| | @Load 2.16 kg, Temperature 230 °C | @Load 4.76 lb, Temperature 446 °F | |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|----------------------|----------------------|----------------------------|
| Hardness, Shore A | 40 | 40 | ASTM D2240 |
| Tensile Strength | 8.1423 MPa | 1180.9 psi | ASTM D412 |
| Elongation at Break | 810 % | 810 % | ASTM D412 |
| Compression Set | 12 % | 12 % | ASTM D395 |
| | @Temperature 23.0 °C | @Temperature 73.4 °F | |
| | 33 % | 33 % | ASTM D395 |
| | @Temperature 70.0 °C | @Temperature 158 °F | |
| | 68 % | 68 % | ASTM D395 rature 212 °F |
| | @Temperature 100 °C | @Temperature 212 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China