

## E-Polymers EFLEX® V2080 SEBS/TPV

Category: Polymer, Thermoplastic, Elastomer, TPE, Styrenic TPE, Thermoplastic Vulcanizate Elastomer (TPV)

## **Material Notes:**

V-series (Thermoplastic Vulcanizate Resins): E-FLEX V series resins are a family of thermoplastic elastomers which exhibit rubber-like properties and are processable on conventional thermoplastic equipment. E-FLEX V series resins are based on EPDM/PP or SEBS/SEEPS/PP(PE) utilizing new reactive grade polyolefins exhibiting high value/cost performance. It shows low temperature toughness, chemical resistance, ozone and UV resistant and wide service temperature range from -55 to 120°C for airbag covers, air dams, license plate holders and interior, as well as weather strip and exterior trim applications in automobile industry, for gasket in construction and appliance industry. Information Provided by E-Polymers Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_E-Polymers-EFLEX-V2080-SEBSTPV.php

| Physical Properties | Metric                               | English                              | Comments   |
|---------------------|--------------------------------------|--------------------------------------|------------|
| Specific Gravity    | 0.904 g/cc                           | 0.904 g/cc                           | ASTM D792  |
| Melt Flow           | 2.0 g/10 min                         | 2.0 g/10 min                         | ASTM D1238 |
|                     | @Load 10.0 kg,<br>Temperature 230 °C | @Load 22.0 lb,<br>Temperature 446 °F |            |

| Mechanical Properties | Metric               | English              | Comments   |
|-----------------------|----------------------|----------------------|------------|
| Hardness, Shore A     | 81                   | 81                   | ASTM D2240 |
| Tensile Strength      | 9.0252 MPa           | 1309.0 psi           | ASTM D412  |
| Elongation at Break   | 600 %                | 600 %                | ASTM D412  |
| Compression Set       | 30 %                 | 30 %                 | ASTM D395  |
|                       | @Temperature 23.0 °C | @Temperature 73.4 °F |            |
|                       | 44 %                 | 44 %                 | ASTM D395  |
|                       | @Temperature 100 °C  | @Temperature 212 °F  |            |

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China