

E-Polymers SEPAZ® C140GP 40% Glass Fiber Reinforced LCP Resin

Category : Polymer , Thermoplastic , Liquid Crystal Polymer (LCP) , Liquid Crystal Polymer (LCP), 40% Glass Fiber Filled

Material Notes:

Liquid Crystal Polymer Resin: SEPAZ LCP resin has a unique structure and performance unthought of in a traditional plastics. Beside SEPAZ LCP takes the excels in all-around performance and molding productivity. SEPAZ LCP has a unique attribute in that the thinner the product becomes, the greater the mechanical strength. SEPAZ LCP finds uses in connectors, sensors and other electronic components and CD pick-up parts, and in copying machine and fax components in office and audio-visual equipment. Information Provided by E-Polymers Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_E-Polymers-SEPAZ-C140GP-40-Glass-Fiber-Reinforced-LCP-Resin.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.71 g/cc	1.71 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength	135.4 MPa	19630 psi	ASTM D638
Elongation at Break	1.3 %	1.3 %	ASTM D638
Flexural Strength	182.47 MPa	26465 psi	ASTM D790
Flexural Modulus	15.60 GPa	2262 ksi	ASTM D790
Izod Impact, Notched	0.785 J/cm	1.47 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	335 °C	635 °F	ASTM D789
Deflection Temperature at 1.8 MPa (264 psi)	271 °C	520 °F	ASTM D648
Flammability, UL94	V-0	V-0	

Processing Properties	Metric	English	Comments
Melt Temperature	350 - 360 °C	662 - 680 °F	
Mold Temperature	30.0 - 95.0 °C	86.0 - 203 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China