

## E-Polymers SEPAZ® N4040M1 Dimensional Stability Heat Resistance Nano Composite Resin

Category : Polymer , Thermoplastic

### Material Notes:

Nanocomposite: SEPAZ Nano PA6 nanocomposites have been prepared successfully in commercial scale through 'in situ' polymerization or melt extrusion. The unique performance properties of nanocomposites provide a great flexibility in materials design. Nanocomposites have been formulated into various resin systems to deliver desired properties: from rheology control to fire retardation. It shows low specific gravity, gas permeability and high heat resistance, rigidity, dimension stability used for underhood and fuel line parts in automotive industry and for packaging film in food industry. Information Provided by E-Polymers Co., Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_E-Polymers-SEPAZ-N4040M1-Dimensional-Stability-Heat-Resistance-Nano-Composite-Resin.php](http://www.lookpolymers.com/polymer_E-Polymers-SEPAZ-N4040M1-Dimensional-Stability-Heat-Resistance-Nano-Composite-Resin.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ASTM D792
Water Absorption	0.40 % @Time 86400 sec	0.40 % @Time 24.0 hour	
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	
Linear Mold Shrinkage, Transverse	0.0080 cm/cm	0.0080 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength	88.78 MPa	12880 psi	ASTM D638
Elongation at Break	1.1 %	1.1 %	ASTM D638
Flexural Strength	125.08 MPa	18141 psi	ASTM D790
Flexural Modulus	8.564 GPa	1242 ksi	ASTM D790
Izod Impact, Notched	0.353 J/cm	0.661 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	165 °C	329 °F	ASTM D648
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Melt Temperature	227 °C	441 °F	
Mold Temperature	40.0 - 60.0 °C	104 - 140 °F	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**