

## E-Polymers SEPAZ® V200L Unfilled PPA

Category : Polymer , Thermoplastic , Polyphthalamide (PPA)

**Material Notes:**

Polyphthal Amide Resin (High Temperature Nylon): SEPAZ PPA is a unique semi-crystalline engineering plastic that bridges the cost-performance gap between traditional engineering thermoplastics and super engineering thermoplastics. SEPAZ PPA resin has excellent mechanical properties (e.g. strength, stiffness, fatigue, creep resistance) over a broad temperature range. In addition to these, special grades formulated for applications requiring flame-retardancy, glycol-resistance, typically for automotive applications, and reflectivity, typically for optoelectronic applications such as high brightness LEDs, are available. Information Provided by E-Polymers Co., Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_E-Polymers-SEPAZ-V200L-Unfilled-PPA.php](http://www.lookpolymers.com/polymer_E-Polymers-SEPAZ-V200L-Unfilled-PPA.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Water Absorption	0.36 %	0.36 %	
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	
Linear Mold Shrinkage, Transverse	0.0070 cm/cm	0.0070 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength	86.03 MPa	12480 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	156.96 MPa	22765 psi	ASTM D790
Flexural Modulus	3.738 GPa	542.1 ksi	ASTM D790
Izod Impact, Notched	0.147 J/cm	0.276 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	138 °C	280 °F	ASTM D648
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Melt Temperature	300 - 330 °C	572 - 626 °F	
Mold Temperature	135 - 160 °C	275 - 320 °F	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**