

## E-Polymers TEKAMID® H14ST Super Toughness PA/ABS Alloy

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS)/Nylon Blend , Nylon

### Material Notes:

Polyamide (Nylon) Resin. TEKAMID is widely being used in manufacturing of automotive and industrial parts with its outstanding mechanical, thermal and chemical properties.H-series: PA6/ABS, PA66/ABS alloy (Unreinforced, GF reinforced, MR reinforced)Information Provided by E-Polymers Co., Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_E-Polymers-TEKAMID-H14ST-Super-Toughness-PAABS-Alloy.php](http://www.lookpolymers.com/polymer_E-Polymers-TEKAMID-H14ST-Super-Toughness-PAABS-Alloy.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792
Water Absorption	0.90 %	0.90 %	
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	
Linear Mold Shrinkage, Transverse	0.0070 cm/cm	0.0070 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength	47.088 MPa	6829.5 psi	ASTM D638
Elongation at Break	100 %	100 %	ASTM D638
Flexural Strength	73.58 MPa	10670 psi	ASTM D790
Flexural Modulus	1.962 GPa	284.6 ksi	ASTM D790
Izod Impact, Notched	7.85 J/cm	14.7 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	ASTM D648
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Melt Temperature	220 °C	428 °F	
Mold Temperature	60.0 - 80.0 °C	140 - 176 °F	

**Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**