

## E-Polymers TEKAMID® TA210HS , Heat Stabilized PA66, DAM

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Heat Stabilized

### Material Notes:

Heat stabilized Information provided by E-Polymers Co. Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_E-Polymers-TEKAMID-TA210HS-Heat-Stabilized-PA66-DAM.php](http://www.lookpolymers.com/polymer_E-Polymers-TEKAMID-TA210HS-Heat-Stabilized-PA66-DAM.php)

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in <sup>3</sup>	ASTM D792
Water Absorption	1.3 %	1.3 %	23°C/24 hr; ASTM D570
Linear Mold Shrinkage	0.015 cm/cm	0.015 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	116	116	ASTM D786
Tensile Strength, Yield	83.0 MPa	12000 psi	ASTM D638
Elongation at Break	60 %	60 %	ASTM D638
Flexural Yield Strength	120 MPa	17400 psi	ASTM D790
Flexural Modulus	3.00 GPa	435 ksi	ASTM D790
Izod Impact, Notched	0.400 J/cm	0.749 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	70.0 µm/m-°C	38.9 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	0.260 W/m-K	1.80 BTU-in/hr-ft <sup>2</sup> -°F	
Melting Point	260 °C	500 °F	ASTM D2133
Deflection Temperature at 0.46 MPa (66 psi)	230 °C	446 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	ASTM D648
Flammability, UL94	V-2	V-2	

Electrical Properties	Metric	English	Comments
Arc Resistance	185 sec	185 sec	Tungsten electrode; ASTM D495

Processing Properties	Metric	English	Comments
Processing Temperature	270 - 290 °C	518 - 554 °F	
Mold Temperature	40.0 - 60.0 °C	104 - 140 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China