

E-Polymers TEKAMID® TA210L Lubricated PA66, DAM

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced

Material Notes:

Lubricated Information provided by E-Polymers Co. Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_E-Polymers-TEKAMID-TA210L-Lubricated-PA66-DAM.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Water Absorption	1.3 %	1.3 %	23°C/24 hr; ASTM D570
Linear Mold Shrinkage	0.015 cm/cm	0.015 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	78	78	ASTM D786
Hardness, Rockwell R	120	120	ASTM D786
Hardness, Shore D	79	79	
Tensile Strength, Yield	85.0 MPa	12300 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Flexural Yield Strength	117 MPa	17000 psi	ASTM D790
Flexural Modulus	3.00 GPa	435 ksi	ASTM D790
Izod Impact, Notched	0.550 J/cm	1.03 ft-lb/in	ASTM D256
Izod Impact, Unnotched	NB @Thickness 3.20 mm	NB @Thickness 0.126 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	70.0 µm/m-°C @Temperature 20.0 °C	38.9 µin/in-°F @Temperature 68.0 °F	ASTM D696
Thermal Conductivity	0.250 W/m-K	1.74 BTU-in/hr-ft ² -°F	
Melting Point	260 °C	500 °F	ASTM D2133
Deflection Temperature at 0.46 MPa (66 psi)	230 °C	446 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	95.0 °C	203 °F	ASTM D648

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Electrical Properties	Metric	English	Comments
Arc Resistance	190 sec	190 sec	Tungsten electrode; ASTM D495

Processing Properties	Metric	English	Comments
Processing Temperature	270 - 280 °C	518 - 536 °F	
Mold Temperature	40.0 - 60.0 °C	104 - 140 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China