

## E-Polymers TEKASTER® F10G30 30% Glass Fiber Reinforced PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled

### Material Notes:

Polyester Resin: TEKASTER is thermoplastic polyester resins (PBT, PET) mostly injection molding. PBT has excellent mechanical properties and well balanced engineering plastics with an electrical performance. Specially G/F reinforced PET has excellent heat resistance, a good surface, chemical resistance and high electrical performance. Information Provided by E-Polymers Co., Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_E-Polymers-TEKASTER-F10G30-30-Glass-Fiber-Reinforced-PBT.php](http://www.lookpolymers.com/polymer_E-Polymers-TEKASTER-F10G30-30-Glass-Fiber-Reinforced-PBT.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.52 g/cc	1.52 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	
Linear Mold Shrinkage, Transverse	0.0090 cm/cm	0.0090 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength	117.72 MPa	17074 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	181.49 MPa	26323 psi	ASTM D790
Flexural Modulus	7.7499 GPa	1124.0 ksi	ASTM D790
Izod Impact, Notched	0.785 J/cm	1.47 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	ASTM D648
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Melt Temperature	230 - 270 °C	446 - 518 °F	
Mold Temperature	60.0 - 80.0 °C	140 - 176 °F	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China